

MM Kwidzyn Sp. z o.o.
ul. Lotnicza 1
82-500 Kwidzyn
Poland

360
THREE SIXTY



KWIDZYN

TECHNICAL DATA SHEET

360 Everyday A3 A4

Parameter	Standard	Unit	Measurement
Substance	EN ISO 536	g/m ²	80 ± 3
Thickness	ISO 534	µm	104 ± 4
Moisture content	EN ISO 287	%	3,5 - 5,0
Whiteness	ISO 11475	CIE units	146 ± 3
Brightness	ISO 2470-2	%	105 ± 2
Opacity	ISO 2471	%	93 +2/-1
Bendtsen Roughness	ISO 8791-2	ml/min	220 ± 60



Product certification

- ✓ 100% ECF Fibres
- ✓ ISO 9706 (Archiving)
- ✓ Production following requirements of DIN EN 12881