

## Kodak Office office paper

Parameter	Unit	Value	Comments
Size		A3, A4	
Grammage	g/m <sup>2</sup>	80 ± 2	Computerized measurement and adjustment. Calibration of measuring heads and parameter control according to PN-ISO 536:1996
Moisture	%	3,8-5,0	Computerized measurement and adjustment. Calibration of measuring heads and parameter control according to PN-ISO 287:1994
Thickness	µm	103 ± 3	PN-EN ISO 534:2005
Whiteness CIE		143 ± 3	PN-ISO 11475:2002 Top and bottom avg
Opacity	%	≥91	ISO 2471:1998
Air Permeability	cm <sup>3</sup> /min	≤1.250	PN-P-50176-3:1994
Smoothness	cm <sup>3</sup> /min	220±60	PN-93/P-50166.02 Top and bottom avg

Conditioning at: RH 50 ± 2 % temp. 23± 1°C PN-EN-20187 :2000

The **Kodak Office** paper produced by International Paper is made from own manufactured Elementary Chlorine Free pulp. Manufacturing process is carried out in neutral environment. Precipitated calcium carbonate used as a filler ensures appropriate alkaline reserve requisite to meet PN-EN ISO 9706:2001 standard "Information and documentation – Paper for documents – Requirements for permanence."